

1730
1731

CONTACT ADHESIVE

CALIFORNIA COMPLIANT BULK



General Description

- California compliant low VOC adhesive designed with outstanding bond and heat strength
- Bonds flatwork (non-postforming) applications
- Minimizes telegraphing
- Spray, brush or roll applied
- Professional use only
- Does NOT require stirring before use

Applications to Avoid

- Copper or copper alloy substrates
- Copper spray system or fluid components
- Surfaces with dirt, grease or excessive moisture
- Vinyl surfaces containing plasticizers which may attack the bond line (conduct pre-testing if in doubt)

Availability

5-gallon pail and 55-gallon drum

Storage/Shelf Life

- Rotate stock and close container when not in use. Store off floor in a cool, well ventilated area and away from exterior walls.
- Shelf life expires 1 year from manufacture date.
- Product may separate after exposure to extreme cold requiring agitation after return to normal temperature.

Coverage Instructions

Cover a minimum of 3.0 dry grams/ft² on each surface.

General Use Instructions

DO NOT USE THIS PRODUCT IF YOU HAVE NOT READ OR DO NOT UNDERSTAND THE WARNINGS, SAFETY MEASURES, AND FIRST AID INSTRUCTIONS PRINTED ON THE CONTAINER OR LABEL. For best results, do not apply the adhesive at temperatures below 65°F.

- Ensure spray system oil and water traps are functioning and are at least 25' from compressor. Allow substrates to acclimate to room temperature for 48 hours before bonding. Assemble glued parts at or above 65°F and ensure each surface is clean and dry.
 - Apply adhesive uniformly to both surfaces in a smooth, pebbled pattern and cover each surface a minimum of 80%. Cover edges 100%. Some porous surfaces may require two (2) coats.
- Allow approximately 3-5 minutes to dry after application and before bonding.
- When ready to bond, surface will be tacky but should not transfer or "leg" to a firmly pressed fingertip. If parts don't stick immediately, they are over-dry and can be reactivated by applying a light coat of fresh adhesive on both parts. Open time is approximately 30 minutes.
- Apply uniform downward pressure (30-40 psi minimum) across the entire bonded surface by mechanical pinch roller (recommended) or by using a 3" wide rubber J-roller. Use of a wooden block or other hand rollers is not recommended.
- Immediate trimming, routing or finishing is possible.
- DO NOT THIN THIS PRODUCT.

Usage Tips and Troubleshooting

- Moisture from condensation must be dried prior to bonding.
- A dull appearance is a symptom of under-applying adhesive. A very shiny appearance or a failed bond is a symptom of inadequate assembly pressure and/or exceeding the open time.

Physical Properties

Color:	Red (1730); Natural (1731)
Viscosity:	1400 cps (typical)
Density:	8.4 lbs/gallon
Solids Content:	36.0% ± 1.0%
VOC (Less water & exempt solvent):	78 g/L (Calculated)
VOC/liter of material:	31 g/L (Calculated)
VHAP Content:	0.03 lbs/lb of solids
Coverage (Spray):	230 bonded ft ² /gal
Flashpoint:	-13.9°C/7.0°F (Closed cup)
Dry Time:	3 - 5 minutes
Open Time:	~30 minutes

*GREENGUARD® Certified

*Complies with SCAQMD, Rule 1168

*Complies with the Ozone Transport Commission (OTC)

*Qualifies for LEED®-NC & CI EQ Credit 3.2:
Construction Indoor Air Quality Management Plan - Before Occupancy

*Qualifies for LEED®-NC & CI EQ Credit 4.1:
Low Emitting Materials: Adhesives & Sealants

*Qualifies for LEED®-NC & CI EQ Credit 4.4:
Laminating adhesives shall contain no added urea-formaldehyde resins.

*Qualifies for LEED®-NC & CI EQ Credit 4.5:
Low Emitting Materials: Furniture and Furnishings

Spray Equipment Instructions

NFPA 33 states non-ASME rated pressure-pot pressure shall not exceed 15 psi when filled with flammable liquids.

- Binks: Hand Gun: Mach 1 HVLP, 95, 7B/C, 62, 69, 2001SS, or 2001; Auto Gun: M95 Auto, M61, M610; Fluid Tip: 97S (HVLP), 63BSS (Hand or Auto Gun); Air Cap: 95P (HVLP), 66SDJG (Hand or Auto Gun)
- DeVilbiss: Hand Gun: JGA 510 or MSA 510; Auto Gun: AGX 550; Fluid Tip: FF (Hand or Auto Gun); Air Cap: 797 (Hand or Auto Gun)
- Graco: Gun: P700, P800, P900; Fluid Tip: 03; Air Cap: 03
- Spee Flo: Gun: 501-149; Fluid Tip: 501-122; Air Cap: 501-122
- General: Fluid Pressure: 10-15 psi; Pump Pressure: 30-50 psi; Air Source: Continuous 60 psi at 20 CFM; Fluid Line: Minimum 3/8" ID*
*This line diameter is critical due to thickness of product.

Clean-up/Disposal

- Clean equipment with finished assembly with WA 130 Adhesive Solvent.
- Dispose of waste in accordance with regulations.

Shipping Information

- Ship Domestic Ground: Adhesives, 3, UN 1133, PG II

Primary Contents

Methyl Acetate (CAS 79-20-9), Parachlorobenzotrifluoride (CAS 98-56-6), Cyclohexane (CAS 110-82-7), Toluene (CAS 108-88-3), Synthetic Rubbers & Resins (Mixture)

Precautionary Information

Refer to product label and material safety data sheet for Health & Safety information before using this product.

Warranty

Manufacturer and distributor of this product makes no warranties, express or implied. No warranty of merchantability or fitness for a particular purpose shall apply. The person using this product (the "user") is solely responsible for determining whether this product is appropriate and/or suitable for user's purpose and method of application. Limitation and exclusion of remedies and damages: the exclusive and sole remedy, and the manufacturer and distributor's exclusive and sole obligation, for any defect of this product is the refund of the purchase price of the product. The manufacturer and distributor shall not, under any circumstances or under any legal theory, be liable to the purchaser or any other person for special, incidental or consequential damages of any nature, including without limitation damages to, or loss of use of, property, damages for loss of profits or revenues or any other damages arising from the purchase or use of the product. The manufacturer and distributor's liability will in no event exceed the purchase price of the product.

Contact

Customer Service: 1-800-433-3222 or adhesives@wilsonart.com
Visit www.wilsonartadhesives.com for information